

EQUINOX GOLD

Tatajuba Drilling - 2018

Hole ID	From (m)	To (m)	Length (m)	Au (g/t)	Cut-off (g/t Au)	Section	Length (m)	Dip	Azimuth	Material
BRAZD644	75.00	78.00	3.00	0.25	0.30	0300E	216.8	-52	358	Fresh Rock
and	98.00	142.00	44.00	1.25	0.30					"
and	149.00	150.00	1.00	0.37	0.30					"
and	162.00	200.00	38.00	4.37	0.30					"
incl	168.00	191.60	23.60	6.04	1.00					"
and	207.00	208.00	1.00	0.87	0.30					"
BRAZD645	86.00	89.00	3.00	0.38	0.30	0250W	170.7	-51	178	Fresh Rock
and	95.00	132.00	37.00	1.36	0.30					"
incl	119.00	130.20	11.20	2.29	1.00					"
and	150.00	151.00	1.00	0.47	0.30					"
BRAZD646	4.00	13.00	9.00	0.47	0.30	0150W	128.2	-60	358	Saprolite
and	17.00	46.00	29.00	1.17	0.30					"
incl	17.00	25.00	8.00	2.07	1.00					"
and	54.00	55.00	1.00	0.56	0.30					Fresh Rock
and	59.00	65.00	6.00	0.61	0.30					"
and	74.00	79.00	5.00	2.06	0.30					"
and	88.00	89.00	1.00	0.47	0.30					"
and	93.00	94.00	1.00	2.07	0.30					"
BRAZD647	2.00	37.00	35.00	1.96	0.30	0150E	81	-50	178	Saprolite
incl	16.20	33.00	16.80	3.59	1.00					"
and	42.00	50.00	8.00	0.74	0.30					"
BRAZD648	92.00	114.20	22.20	1.11	0.30	0200W	119.1	-52	178	Fresh Rock
incl	96.00	99.00	3.00	2.42	1.00					"
incl	107.00	113.00	6.00	1.51	1.00					"
BRAZD649	36.00	37.00	1.00	0.32	0.30	0200E	154.35	-53	178	Saprolite
and	126.00	135.00	9.00	0.34	0.30					Fresh Rock
and	144.20	145.00	0.80	4.31	0.30					"
BRAZD650	59.00	66.00	7.00	0.42	0.30	0150E	140.1	-50	178	Saprolite
and	88.00	96.00	8.00	2.18	0.30					Fresh Rock
and	104.00	113.00	9.00	0.51	0.30					"
and	118.00	119.00	1.00	0.42	0.30					"
and	132.00	137.00	5.00	0.45	0.30					"
BRAZD651	78.00	79.00	1.00	0.64	0.30	0100E	143.5	-56	178	Fresh Rock
and	97.00	116.00	19.00	1.42	0.30					"
BRAZD652	10.00	11.00	1.00	1.96	0.30		170.3	-50	106	Saprolite
and	16.00	17.00	1.00	0.51	0.30					"
and	25.00	26.00	1.00	0.51	0.30					"
and	31.00	35.00	4.00	1.88	0.30					"
and	39.00	45.00	6.00	0.37	0.30					"
and	75.00	76.00	1.00	2.55	0.30					Fresh Rock
and	84.65	95.00	10.35	2.55	0.30					"
incl	85.85	88.00	2.15	2.68	1.00					"
incl	90.90	95.00	4.10	4.76	1.00					"
and	99.00	108.00	9.00	0.57	0.30					"
and	113.80	117.20	3.40	1.62	0.30					"
and	141.20	144.90	3.70	0.50	0.30					"
and	149.80	159.60	9.80	1.07	0.30					"
incl	149.80	152.00	2.20	3.39	1.00					"
and	163.30	169.30	6.00	1.66	0.30					"
incl	166.30	169.30	3.00	2.99	1.00					"
BRAZD653	6.00	7.00	1.00	0.39	0.30	0200W	170.95	-60	178	Saprolite
and	34.00	35.00	1.00	0.56	0.30					Transition
and	101.00	102.00	1.00	0.51	0.30					Fresh Rock
and	109.60	138.00	28.40	1.11	0.30					"
and	143.00	149.00	6.00	1.09	0.30					"
and	169.80	170.95	1.15	0.30	0.30					"
BRAZD654	106.60	107.40	0.80	0.84	0.30	0250W	173.95	-60	178	Fresh Rock
and	109.00	129.00	20.00	2.09	0.30					"
incl	114.00	127.40	13.40	2.77	1.00					"
and	136.00	147.00	11.00	0.42	0.30					"
and	153.80	154.80	1.00	7.56	0.30					"
BRAZD655	7.00	10.00	3.00	0.55	0.30	000W	135.45	-52	178	Saprolite
and	63.00	67.40	4.40	0.43	0.30					Fresh Rock
and	103.00	112.90	9.90	0.80	0.30					"

Qualified Person and Disclosure Statement

Scott Heffernan, M.Sc., P.Geo., the Company's EVP Exploration and Qualified Person under National Instrument 43-101, has reviewed and verified that the technical information contained in this document is accurate and approves the written disclosure of the same. Drill composites were calculated using cut-off values of 0.3 g/t, 1.0 g/t or 5.0 g/t gold as specified in the drill table and contain no more than 5 metres of internal waste. Drill intersections are calculated using uncut assays and are reported as drilled thicknesses. True widths of the mineralized intervals are interpreted to be 60 to 90 percent of the reported lengths. All samples were submitted to ALS Chemex in Belo Horizonte, Brazil for sample preparation. Sample pulps were then sent to ALS Chemex in Lima, Peru for geochemical analysis for gold by fire assay of a 30-gram charge with an Atomic Absorption finish (AA) and for a 33 multi-element geochemical suite by 4-acid digestion and Inductively-Coupled Mass Spectrometry (ICP-MS). Samples with AA gold values over 10.0 g/t are re-assayed by Screen Metallics fire assay. Control samples (accredited standards, blanks and duplicate samples at the field and preparation stages) were inserted on a regular basis. Results were monitored upon receipt of assays.

EQUINOX GOLD

Tatajuba Drilling - Select Historical Results

Hole ID	From (m)	To (m)	Length (m)	Au (g/t)	Cut-off (g/t Au)	Section	Length (m)	Dip	Azimuth	Material
BRAZD114	66.00	120.20	54.20	2.78	0.30	0300E	130.45	-50	358	Fresh Rock
incl	91.00	117.00	26.00	4.27	1.00					"
BRAZD116	38.20	46.70	8.50	1.89	0.30	0100E	116.3	-50	178	Saprolite
incl	40.50	44.50	4.00	3.44	1.00					"
BRAZD120	42.00	47.00	5.00	0.83	0.30	0500E	114.56	-50	178	Saprolite
BRAZD121	66.00	75.52	9.52	1.84	0.30	0100W	109.66	-50	178	Fresh Rock
incl	67.70	69.45	1.75	8.11	1.00					"
BRAZD122	38.42	53.10	14.68	1.38	0.30	0300W	95.22	-50	178	Saprolite
incl	46.00	53.10	7.10	1.86	1.00					"
BRAZD123	35.40	41.11	5.71	0.36	0.30	0500W	78.75	-50	178	Transition
BRAZD131	40.00	68.40	28.40	0.87	0.30	0200E	98.65	-50	178	Transition
incl	57.11	61.00	3.89	2.81	1.00					"
BRAZD133	54.00	61.95	7.95	2.44	0.30	000W	86.8	-50	178	Fresh Rock
incl	57.17	61.95	4.78	3.79	1.00					"
BRAZD139	43.00	47.00	4.00	0.30	0.30	0250E	70.4	-50	178	Saprolite
BRAZD142	0.00	9.71	9.71	1.76	0.30	0200W	58.73	-50	178	Saprolite
incl	0.00	4.07	4.07	2.90	1.00					"
and	16.97	52.00	35.03	2.81	0.30					"
incl	25.33	33.18	7.85	10.55	1.00					"
incl	49.00	50.87	1.87	3.85	1.00					"
BRAZD161	67.00	69.00	2.00	0.86	0.30	0350W	79	-50	178	Transition
BRAZD162	47.37	56.45	9.08	1.94	0.30	0150W	77.75	-50	178	Fresh Rock
incl	54.00	55.50	1.50	7.97	1.00					"
BRAZD164	40.00	57.00	17.00	2.32	0.30	0250W	97.7	-50	178	Transition
incl	40.00	45.00	5.00	6.19	1.00					"
BRAZD167	43.00	59.15	16.15	1.73	0.30	0150E	81.4	-50	178	Saprolite
incl	43.75	52.85	9.10	2.68	1.00					"
BRAZD171	47.50	55.42	7.92	2.95	0.30	0050E	99.5	-50	178	Fresh Rock
BRAZD173	29.70	33.50	3.80	0.78	0.30	0400W	126.15	-50	178	Saprolite
BRAZD236	50.00	83.50	33.50	1.05	0.30	0200W	130.3	-50.43	177.55	Transition
incl	60.00	73.00	13.00	1.42	1.00					"
incl	82.00	83.50	1.50	6.29	1.00					"
BRAZD237	51.00	78.00	27.00	2.31	0.30	0250W	140.2	-50.15	178.26	Fresh Rock
incl	59.65	75.00	15.35	3.03	1.00					"
BRAZD238	11.00	42.00	31.00	1.49	0.30	0150W	130.5	-59.65	358.6	Transition
incl	13.00	16.55	3.55	3.29	1.00					Saprolite
incl	35.00	39.00	4.00	2.40	1.00					Transition
BRAZD240	0.00	12.00	12.00	1.14	0.30	0250W	74.6	-49.89	178.3	Saprolite
incl	9.00	11.00	2.00	3.81	1.00					"
and	21.00	41.00	20.00	1.30	0.30					"
incl	21.00	24.00	3.00	2.36	1.00					"
incl	32.00	40.00	8.00	1.75	1.00					"
BRAZD241	31.00	48.00	17.00	2.06	0.30	0050W	81.05	-49.71	357.79	Saprolite
incl	31.00	39.00	8.00	2.60	1.00					"
incl	42.00	47.00	5.00	2.31	1.00					"
BRAZD242	27.00	39.00	12.00	4.06	0.30	000W	80.25	-50.37	358.19	Saprolite
incl	27.00	30.00	3.00	4.80	1.00					"
incl	34.00	37.00	3.00	10.74	1.00					"
BRAZD243	0.00	4.00	4.00	0.45	0.30	0100W	90.45	-49.9	178.01	Laterite
and	14.00	45.00	31.00	0.94	0.30					Transition
incl	31.00	37.00	6.00	1.45	1.00					"
incl	43.00	44.00	1.00	4.36	1.00					"
BRAZD244	78.00	98.00	20.00	1.31	0.30	0100E	145.2	-49.91	178.13	Fresh Rock
incl	79.00	95.00	16.00	1.51	1.00					"
BRAZD245	84.00	89.55	5.55	2.27	0.30	0050E	135.2	-50.09	178.88	Fresh Rock
incl	85.00	89.00	4.00	2.83	1.00					"
BRAZD246	59.00	70.00	11.00	1.33	0.30	0150E	120.25	-49.88	178.17	Transition
incl	60.40	70.00	9.60	1.44	1.00					"
BRAZD247	3.10	50.00	46.90	1.17	0.30	0150E	80.55	-49.78	177.96	Saprolite
incl	13.55	31.00	17.45	2.36	1.00					"
BRAZD248	72.00	91.40	19.40	1.49	0.30	0200E	130.5	-50.22	178.28	Fresh Rock
incl	85.00	91.00	6.00	3.86	1.00					"
BRAZD250	21.00	56.00	35.00	13.74	0.30	0300E	150.55	-50.44	358.28	Saprolite
incl	23.00	42.00	19.00	16.15	1.00					"
incl	47.00	55.00	8.00	21.21	1.00					Transition
BRAZD251	94.00	128.00	34.00	1.43	0.30	0300E	161.1	-50.28	358.07	Fresh Rock
incl	96.00	118.00	22.00	1.94	1.00					"

6422.47

Qualified Person and Disclosure Statement

Scott Heffernan, M.Sc., P.Geo., the Company's EVP Exploration and Qualified Person under National Instrument 43-101, has reviewed and verified that the technical information contained in this document is accurate and approves the written disclosure of the same. Drill composites were calculated using cut-off values of 0.3 g/t, 1.0 g/t or 5.0 g/t gold as specified in the drill table and contain no more than 5 metres of internal waste. Drill intersections are calculated using uncut assays and are reported as drilled thicknesses. True widths of the mineralized intervals are interpreted to be 60 to 90 percent of the reported lengths. All samples were submitted to ALS Chemex in Belo Horizonte, Brazil for sample preparation. Sample pulps were then sent to ALS Chemex in Lima, Peru for geochemical analysis for gold by fire assay of a 30-gram charge with an Atomic Absorption finish (AA) and for a 33 multi-element geochemical suite by 4-acid digestion and Inductively-Coupled Mass Spectrometry (ICP-MS). Samples with AA gold values over 10.0 g/t are re-assayed by Screen Metallica fire assay. Control samples (accredited standards, blanks and duplicate samples at the field and preparation stages) were inserted on a regular basis. Results were monitored upon receipt of assays.